

SN 10/824,691Docket No. S-102,389In Response to Office Action dated May 16, 2005

## AMENDMENTS TO THE CLAIMS:

Please amend the claims as shown below. This listing of claims will replace all prior versions, and listings, of claims in the application.

## LISTING OF CLAIMS:

1-5. (cancelled)

6. (currently amended) A process for preparing a bulk, superhard, nanocomposite compact ~~consisting essentially of nanocrystalline grains of at least one high pressure phase of B-C-N surrounded by amorphous, diamond-like carbon grain boundaries, comprising the steps of:~~

- (a) ball milling a mixture of graphite and hexagonal boron nitride to produce a ball-milled mixture of amorphous and/or nanocrystalline graphitic carbon and boron nitride, the ball-milled mixture comprising amorphous boron nitride, nanocrystalline boron nitride or mixtures thereof, the ball-milled mixture further comprising amorphous carbon, nanocrystalline graphitic carbon or mixtures thereof;
- (b) encapsulating the ball-milled mixture at a pressure in the range of from about 15 GPa to about 25 GPa; and
- (c) sintering the encapsulated ball-milled mixture ~~at a pressure of about 5-25 GPa and a temperature of about 1000-2500 K, thereby producing a bulk, superhard nanocomposite compact consisting essentially of~~ nanocrystalline grains of at least one ternary phase of B-C-N surrounded by amorphous diamond-like carbon grain boundaries.

7. (original) The process of claim 6, wherein the ball milled mixture of graphite hexagonal boron nitride consists essentially of about 1-4 parts graphite to about 1 part hexagonal boron nitride.

8. (withdrawn) The process of claim 7, wherein the ball milled mixture of graphite and hexagonal boron nitride consists essentially of about 1 part graphite to about 1 part hexagonal boron nitride.

SN 10/824,691

Docket No. S-102,389

In Response to Office Action dated May 16, 2005

9. (withdrawn) The process of claim 7, wherein the ball milled mixture of graphite and hexagonal boron nitride consists essentially of about 2 parts graphite to about 1 part hexagonal boron nitride.
10. (original) The process of claim 7, wherein the ball milled mixture of graphite and hexagonal boron nitride consists essentially of 4 parts graphite to about 1 part hexagonal boron nitride.
11. (cancelled)
12. (original) The process of claim 7, wherein the encapsulated ball-milled mixture is sintered at a pressure of about 15-25 GPa and at a temperature of about 2000-2500 K.
13. (original) The process of claim 7, wherein the encapsulated ball-milled mixture is sintered at a pressure of about 16-25 GPa and at a temperature of about 2100-2500 K.
14. (original) The process of claim 7, wherein the encapsulated ball-milled mixture is sintered at a pressure of about 20-25 GPa and at a temperature of about 2000-2500 GPa.
15. (original) The process of claim 7, wherein the encapsulated ball-milled mixture is sintered at a pressure of about 20-25 GPa and at a temperature of about 2100-2400 K.
16. (original) The process of claim 7, wherein the encapsulated ball-milled mixture is sintered at a pressure of about 20 GPa and at a temperature of about 2000-2400 K.
17. (withdrawn) The process of claim 7, wherein the encapsulated ball-milled mixture is sintered at a pressure of about 25 GPa and at a temperature of about 2100-2300 K.
18. (amended) The process of claim 6, wherein step (b) comprises encapsulating the amorphous ball-milled mixture in capsule comprising platinum, gold, rhenium, or boron nitride.
19. (original) The process of claim 7, wherein said compact has a Vickers hardness of about 41-68 GPa.

SN 10/824,691

Docket No. S-102,389

In Response to Office Action dated May 16, 2005

20. (original) The process of claim 7, wherein said compact has a Vickers hardness of about 50-68 GPa.
21. (original) The process of claim 7, wherein said compact has a Vickers hardness of about 62-68 GPa.
22. (original) The process of claim 7, wherein said compact has a Vickers hardness of 68 GPa.
- 23-43. (cancelled)